

A lacquer for panel and spot repair and over-all refinishing of automotive vehicle having nitrocellulose lacquer or baked enamel finishes. If used over acrylic lacquer finishes it should be limited to complete refinishing.

DIRECTIONS FOR USE
STIR THOROUGHLY TO SECURE UNIFORM MIXTURE

NITROCELLULOSE LACQUER THINNER RECOMMENDED

PAINT SHOULD BE MIXED "BY COLOR" IN A LARGE CONTAINER AND THEN RETURNED TO GALLON CANS TO INSURE COLOR UNIFORMITY.

Where possible all parts should be painted at one time to insure uniformity because there are many variables that will change the color such as weather, thinners, spray gun conditions, etc.

THINNING: Thin 1 part of Nitrocellulose Lacquer with 1½ parts of Nitrocellulose Lacquer Thinner, selecting from a different grade depending on temperature, weather, and/or topcoating to provide improved leveling, flow-out and gloss.

APPLICATION: Non-metallic colors: Spray 3 or 4 wet double coats, one immediately after the other. Wait 15-20 minutes between coats and proceed.

Metallic Colors: Secure hiding by spraying 2 double coats, one immediately after the other. Follow with 3 and 4 lighter single coats, thinned 1 part of Nitrocellulose Lacquer with 3 parts Nitrocellulose Lacquer Thinner. **Note:** Cross-coating may be necessary to insure proper metallic flow-out.

RUBBING: Allow to dry at least 24 hours, then proceed with Hand Rubbing Compound or machine Polishing Compound. Hand polish or dry-buff with polishing disc or lambs wool bonnett.

WAXING: Allow at least 90 days for the paint to cure prior to applying any type of wax.

WARNING! FLAMMABLE, VAPORS AND MISTS HARMFUL.

Any and all personal health and safety precautions must be used. Keep away from heat, sparks, open flame and other sources of ignition. Avoid breathing vapor or spray mist and prolonged contact with skin. Wash thoroughly after handling and before eating or smoking. Keep container closed when not in use. Use with proper and adequate ventilation. Store container in safe location, and away from children.

LIMITED WARRANTY

Buyer agrees that if the product proves to be defective, Hibernia's only obligation shall be to replace or refund the purchase price of such product as directed. Hibernia shall not be liable in tort or contract for any loss or damage, direct, incidental or consequential.